



經濟部標準檢驗局

台北市濟南路一段四號

THE BUREAU OF STANDARDS, METROLOGY AND INSPECTION

MINISTRY OF ECONOMIC AFFAIRS, REPUBLIC OF CHINA

4 CHINAN ROAD, SECTION 1, TAIPEI, 100, TAIWAN

TEL : (02)2343-1700 FAX : (02)2393-2324

WEB SITE : WWW.BSMI.GOV.TW

TEST REPORT

Report Number: 90604100218

Application Date: 31 MAR 2005

Issue Date: 26 APR 2005

Laboratory: Tainan Branch

Address: 179 Peimen Road, Section 1, Tainan, 700, Taiwan

Applicant: Vivaldi Ltd.

Address: (Null)

COPY

Product: PVC WALL PANEL

Specifications: 250m/m width X 8m/m thickness

Model: (Null)

Results of the test are detailed in the attached page(s) and apply only to the sample(s) teste

This test report contains 2 pages and cannot be reproduced, except in full, without the written approval of the laboratory.

M. S. Li


Signatory of Report

Y. C. Li

Head of Laboratory

Y. C. Li

Authorized Signatory - Director General
The Bureau of Standards, Metrology and Inspection



TEST REPORT



Report Number : 90604100218

Page : 1 of 1 Page(s)

Applicant : Vivaldi Ltd.

Product : PVC WALL PANEL

Specifications : 250m/m width X 8m/m thickness

Model : (Null)

Application Date : 31 MAR 2005

Completion Date: 26 APR 2005

Test Items	Results
Flammability(The heating period of time : 10sec)	
The length of carbonization	6.5cm
Remaining flame	0.8sec
Afterglow	2.3sec
<p>Test Description :</p> <p>Pretreatment of Specimen : CNS7614 A3125 Method A.</p> <p>Test Method : CNS7614 A3125.</p> <p>Test Result : The test Items were complied with CNS 7614 A3125 Anti-flamming Grade 2 of heating 10 sec.</p>	